

# FLEXI-DECK 500-E

100% SOLIDS FLEXIBLE EPOXY PRIMER & COATING

## DESCRIPTION:

Edison **FLEXI-DECK 500-E** is a 100% solids modified epoxy elastomeric membrane/coating and primer, designed for high performance under a wide range of application and service conditions.

**FLEXI-DECK 500-E** features odorless application, “zero” VOC content, low viscosity and self-priming to concrete, steel, aluminum, ceramic tile\*, plywood, natural stone, glass\*, vinyl tile and may other substrates. (\*Note: Some glassy surfaces require use of **Type G** adhesion promoting additive.) Clear or a wide range of colors is available.

*Common uses for FLEXI-DECK 500-E include:*

- **PARKING DECK WATERPROOFING MEMBRANES**



- **DECK AND BALCONY WATERPROOFING**
- **NON-SLIP SURFACING**
- **TANK LINING & SECONDARY CONTAINMENT**

- **INDUSTRIAL FLOORING UNDER-LAYMENT**
- **MECHANICAL ROOM FLOORING**

## APPLICATION

**Surface Preparation:** Surfaces to be coated are best if clean and dry, free of grease, oil, dirt, and other contaminants. If product will be applied over smooth or previously coated surfaces, a test application should be performed to assure adhesion and compati-

bility. For specific alternate procedures for contaminated or coated surfaces, consult your Edison Coatings Representative. Detailing of cracks, joints, drains, perimeters and penetrations should be performed as stated in the **FLEXI-DECK 500** installation manual.

**Thinning & Mixing:** **FLEXI-DECK 500-E** is supplied as a low viscosity, two-component, 100% solids coating. For most applications, no thinning is required. In some cases thinning may be economically advantageous, to increase product spread rate. In other cases, slight solvent addition may improve the “bite” on a hard existing coating or may improve penetration of slightly oily surfaces. Thinning should be limited to the minimum required, typically about 5-10% solvent addition should be sufficient. Use only compatible solvents, such as xylene or methyl ethyl ketone. **Caution: Solvents are hazardous materials and must be handled in accordance with the safety guidelines published by their manufacturers.**

Mix ratio is nominally 1:1 resin to hardener by volume. Measure and mix consistently. Product is also available in pre-measured units, eliminating the need for field-measuring of components. Mix tho roughly for at least two minutes, scraping the container bottom and sides to assure complete mixing. There is no induction or waiting time required after mixing before application.

The exothermic nature of epoxy setting reactions may cause rapid temperature rise when the mixture is left massed in a pail, resulting in high temperatures and loss of utility of the product. To maximize handling and working time, pour the mixture into shallow pans or dump and squeegee the mixture out onto the surface to be coated within a few minutes of mixing.

Manufactured by: EDISON COATINGS, INC., 3 Northwest Drive, Plainville, CT 06062

Phone: (860) 747-2220

Toll-Free: (800) 341-6621

Internet: [www.edisoncoatings.com](http://www.edisoncoatings.com)

Apply by brush, roller, squeegee or plural component spray. Clean tools and equipment immediately after use with xylene. Do not subject to immersion for at least 5 days after application, or discoloration may result.

**TECHNICAL DATA:**

<b>Composition</b>	<b>100% Solids Modified Epoxy; "0" V.O.C.</b>
<b>Mix Ratio</b>	<b>1:1 by Volume</b>
<b>Viscosity</b>	<b>220-450 cps</b>
<b>Pot Life</b>	<b>20-30 mins. at Room Temp.</b>
<b>Coverage</b>	<b>80-120 sq. ft./gal. per coat</b>
<b>Film Build</b>	<b>40-70 mils (2 coats plus anti-skid aggregate)</b>
<b>Elongation</b>	<b>110%</b>
<b>Tensile Strength</b>	<b>1240 psi</b>
<b>Colors</b>	<b>Black, Medium Grey M1, Custom Colors</b>

**SAFETY**

**Read and observe the safety and handling guidelines as detailed in the Material Safety Data Sheets supplied with this product.** Avoid skin and eye contact. Epoxy resins are potential sensitizers, although Edison Coatings, Inc. avoids the use of the most highly sensitizing BGE and CGE diluents in this product. Hardener is a Corrosive Liquid. Avoid skin and eye contact. Remove from skin immediately, in case of contact. Remove contaminated shoes and clothing immediately.

**FOR COMMERCIAL & INDUSTRIAL USE ONLY.**

Rev. 8/2015



**3 Northwest Drive, Plainville, CT 06062**

**Phone: (860) 747-2220 or (800) 341-6621**

**Fax: (860) 747-2280**

**E-mail: [edisoncoatings@outlook.com](mailto:edisoncoatings@outlook.com)**

**Internet: [www.edisoncoatings.com](http://www.edisoncoatings.com)**

Edison Coatings products are for commercial use only. In case of defect in manufacture or packaging, materials will be replaced at no cost. No other warranty, except for such replacement, express or implied, is in effect. Any implied warranty of merchantability or fitness for a particular purpose is expressly disclaimed. Although information and advice supplied in this publication are believed to be reliable, they do not represent performance specifications and no obligation or liability is assumed for advice given or results obtained. Product formulations and performance characteristics are subject to change without notice. Other conditions and limitations may be imposed at time of sale.