

FLEXI-GARD 500-N

CHEMICAL-RESISTANT NOVOLAC/BIS F EPOXY COATINGS

DESCRIPTION

FLEXI-GARD 500-N coatings are 100% solids, odorless, heavy duty Novolac/Bis F epoxy coatings designed for protection of concrete floors and decks from acids, solvents and other aggressive chemical exposures. They are available in clear or pigmented versions.

FLEXI-GARD 500-N Standard Formula is a 100% solids, low viscosity, odorless Novolac/Bis F epoxy coating designed for a wide range of chemical exposures, including strong inorganic acids.

FLEXI-GARD 500-N Skydrol Resistant Formula is designed to provide higher resistance to solvents and petroleum distillates such as jet fuel, xylene and ethanol.

FLEXI-GARD 500-N-FLX Flexibilized Formula is a 100% solids, medium viscosity, odorless Novolac/Bis F/urethane-epoxy designed for use as an underlayment on surfaces subject to deflection or thermal cycling.

ADVANTAGES:

- ✓ **Ease of application** by roller or appropriate spray equipment assures consistent results and high productivity.
- ✓ **Fast strength development** allows minimum downtime and quick return to service, even in heavy traffic exposures.
- ✓ **High strength** permits long-term performance in forklift and other vehicular traffic exposures.
- ✓ **High gloss and clarity** permit the achievement of excellent aesthetic results.
- ✓ **High chemical resistance** (Refer to chemical resistance charts).

TECHNICAL DATA:

PROPERTY	500-N, 500-N Skydrol-Resist	500-N-FLX
Composition	100% Solids Novolac/Bis F Modified Epoxy; "0" V.O.C.	100% Solids Urethane/ Novolac/Bis F Modified Epoxy
Mix Ratio	3:1 by Volume	1:1 by Volume
Viscosity	450-850 cps	850-1550 cps
Pot Life	20-30 mins. at Room Temp.	20-30 mins. at Room Temp.
Coverage	60-100 sq. ft./gal. per coat	40-80 sq. Ft./gal. Per coat
Film Build	15-25 mils per coat (does not include optional anti-slip aggregate)	20-40 mils per coat
Elongation	1%	10%
Tensile Strength	2000 psi	1000 psi

APPLICATION

Surface Preparation: Surfaces to be coated are best if clean and dry, free of grease, oil, dirt, and other contaminants. If product will be applied over smooth or previously coated surfaces, a test application should be performed to assure adhesion and compatibility. For specific alternate procedures for contaminated or coated surfaces, consult your Edison Coatings Representative. Detailing of cracks, joints, drains, perimeters and penetrations should be performed as stated in the **FLEXI-GARD 500** installation manual. Slabs on grade should always be pretested for moisture vapor drive in multiple locations prior to coating. Slabs exhibiting vapor emission rates in

excess of 3 lbs./1000 sq.ft./24 hours shall be deemed unsuitable for coating unless remediated.

Thinning & Mixing: *FLEXI-GARD 500N* is supplied as a two-component, 100% solids coating. For most applications, no thinning is required. In some cases thinning may be economically advantageous, to increase product spread rate. In other cases, slight solvent addition may improve the “bite” on a hard existing coating or may improve penetration of slightly oily surfaces. Thinning should be limited to the minimum required, typically about 5-10% solvent addition should be sufficient. Use only compatible solvents, such as xylene or methyl ethyl ketone. **Caution: Solvents are hazardous materials and must be handled in accordance with the safety guidelines published by their manufacturers.**

Mix ratio is nominally 3:1 resin to hardener by volume for *500-N* and *500-N Skydrol-resistant*; 1:1 for *500N-FLX*. Measure and mix consistently. Product is also available in pre-measured units, eliminating the need for field-measuring of components. Mix thoroughly for at least two minutes, scraping the container bottom and sides to assure complete mixing. There is no induction or waiting time required after mixing before application.

The exothermic nature of epoxy setting reactions may cause rapid temperature rise when the mixture is left massed in a pail, resulting in high temperatures and loss of utility of the product. To maximize handling and

working time, pour the mixture into shallow pans or dump and squeegee the mixture out onto the surface to be coated within a few minutes of mixing.

Apply by brush, roller, squeegee or plural component spray. Clean tools and equipment immediately after use with xylene. Do not subject to immersion for at least 5 days after application, or discoloration may result.

SAFETY

Read and observe the safety and handling guidelines as detailed in the Material Safety Data Sheets supplied with this product. Avoid skin and eye contact. Epoxy resins are potential sensitizers, although Edison Coatings, Inc. avoids the use of the most highly sensitizing BGE and CGE diluents in this product. Hardener is a Corrosive Liquid. Avoid skin and eye contact. Remove from skin immediately, in case of contact. Remove contaminated shoes and clothing immediately.

FOR COMMERCIAL & INDUSTRIAL USE ONLY.

Rev. 4/2005



3 Northwest Drive, Plainville, CT 06062

Phone: (860) 747-2220 or (800) 697-8055

E-mail: edison@edisoncoatings.com

Fax: (860) 747-2280 or (800) 697-8044

Internet: www.edisoncoatings.com

Edison Coatings products are for commercial use only. In case of defect in manufacture or packaging, materials will be replaced at no cost. No other warranty, except for such replacement, express or implied, is in effect. Any implied warranty of merchantability or fitness for a particular purpose is expressly disclaimed. Although information and advice supplied in this publication are believed to be reliable, they do not represent performance specifications and no obligation or liability is assumed for advice given or results obtained. Product formulations and perfor-