

REPLIC-8

Custom Cement-Based Replication Mixes for Historic Concrete & Other Substrates

Repair Mortars, Stuccos, Casting Compounds & Historic Concretes
Natural Cement, Natural Hydraulic Lime or Portland Cement Binders

DESCRIPTION:

REPLIC-8 is a series of custom-formulated replication mixes for repair or replacement of historic concrete and other cementitious substrates.

REPLIC-8 provides esthetically and mechanically compatible repair or replacement for substrates weakened by weathering, carbonation or degradation of cementitious components.

REPLIC-8 incorporates binders and aggregates matching original materials, maintaining historic integrity and assuring long-term retention of color and match to original materials.

Esthetic & Performance Requirements

REPLIC-8 mixes meet all of the esthetic and performance criteria for effective replication mixes:

- ◆ *Matches Color & Texture*
- ◆ *Match Strength and Permeability of Original Materials*
- ◆ *Match Fine and Coarse Aggregates, Remaining a Close Match as it Ages and Weathers*
- ◆ *May Be Adjusted to Meet Air Entrainment & Water Reduction Requirements*

Performance

REPLIC-8 mix designs are generally non-proprietary. They can be produced to conform with any specification, or can be developed through analysis of existing materials. Minimum strengths and other parameters can also be specified.



Photo: The Madison Avenue Bridge on Connecticut's National Landmark Merritt Parkway had repair sections repoured using **REPLIC-8**, custom-matched by Edison Coatings, Inc..



Compatible Substrates

Concrete, cast stone, stucco, precast concrete, acoustical tile, pavers, exposed aggregate wall systems and others

APPLICATION:

The range of materials and applications covered under the **REPLIC-8** label are too diverse to allow a universal, comprehensive set of application instructions to be published herein.

The following are some general comments and guidelines:

Maximum Application Temperature: 30°C (86°F)

Minimum Application Temperature: 10°C (50°F)

1. **Surface Preparation:** When applying **REPLIC-8** to other substrates, they should be clean, damp or surface-dry, free of grease, oil, dirt, organic coatings or other materials which may interfere with adhesion.

2. **Application:** Consult your Edison Coatings Technical Representative for guidance and recommendations on how to best use your particular **REPLIC-8** formulation to achieve your particular project goals.

Typical Coverage Rates:

Supersack packaging generally corresponds with yields of 1 cubic yard.

Small bag or bucket packaging generally corresponds with 1/2 cubic foot yield.

3. Curing:

Observe the curing guidelines developed for your formulation and application. Generally, formed and poured materials can be left to cure in their forms for 3-7 days. Exposed materials should be misted several times a day for at least the first 3 days.

Do not apply when rain is anticipated within 12 hours of application, and protect, if necessary, during that 12-hour cure period. Protect from freezing for at least 72 hours.

4. **Compatibility:** Do not apply without protecting surfaces or materials which may be damaged by contact.

5. **Safety & Handling:** **REPLIC-8** products may contain cement, lime and other alkaline materials. Avoid skin and eye contact and use personal protective equipment as instructed in the product Safety Data Sheet (SDS). Carefully read and observe all safety and handling guidelines as detailed in the Safety Data Sheets supplied with this product.

Rev. 8/2015



3 Northwest Drive, Plainville, CT 06062 Phone: (860) 747-2220 or (800) 341-6620

E-mail: info@edisoncoatings.com

Internet: www.edisoncoatings.com

Edison Coatings products are for commercial use only. In case of defect in manufacture or packaging, materials will be replaced at no cost. No other warranty, except for such replacement, express or implied, is in effect. Any implied warranty of merchantability or fitness for a particular purpose is expressly disclaimed. Although information and advice supplied in this publication are believed to be reliable, they do not represent performance specifications and no obligation or liability is assumed for advice given or results obtained. Product formulations and performance characteristics are subject to change without notice. Other conditions and limitations may be imposed at time of sale.