

MX-C 25 MASONRY

**Fibre-reinforced inorganic matrix
for FRCM strengthening solutions
on masonry
CAM certified (recycled content)**



FIELDS OF APPLICATION

Inorganic matrix for use with Ruregold FRCM system carbon meshes for:

- Retrofitting and upgrading the static and seismic behaviour of masonry buildings.
- Structural strengthening of load-bearing walls (piers) and perimeter strips (spandrels) in masonry buildings.
- Structural strengthening of masonry corners and floor edge beams.
- Structural strengthening of eaves edge beams in masonry walls.
- Structural strengthening of masonry arches, vaults, and domes.
- Structural strengthening of masonry infrastructure.
- Increased ductility of masonry buildings.
- Internal partition and external infill wall anti-overtum protection.

METHOD OF USE

Preparing the inorganic matrix

MX-C 25 Masonry does not require any additional material and may be prepared using:

- A planetary type mixer.
- A concrete mixer (do not exceed 60% of the nominal load limit and mix with the axis of rotation almost horizontal).
- A screw mixer (e.g. Gras Calce **Turbomalt** mixer).
- The product may also be mixed manually in a bucket using a paddle mixer, pouring in a part of the contents of the bag and adding the appropriate quantity of water.

Mix as follows:

1. Pour in the contents of the bag of **MX-C 25 Masonry** and add approx. 5.5-6.5 litres of clean water.
2. Mix for about 3-4 minutes (4-5 minutes when using a concrete mixer) to obtain a smooth, homogeneous mix.
3. Leave the mix to stand for about 1-2 minutes before use.

FINISHING

Once the mortar is fully cured, apply the appropriate finishing, provided it does not contain chalk.

IDENTIFICATION DATA

Classification EN 998-2:2016	G - Guaranteed performance masonry mortar for general use on elements subject to structural requirements
Grain size of aggregates	0 - 3 mm (0 – 0.1181 in)
Density of fresh mortar (EN 1015-6)	Approx. 1750 kg/m ³ (109.2 lb/ft ³)
Certification	CVT n. 285 del 28/06/2023 according to 'Guidelines for the identification, qualification and acceptance control of fibre-reinforced composites with inorganic matrix (FRCM) to be used for the structural consolidation of existing buildings' in combination with C-MESH 84/84
Content of recovered, recycled and sub-product material	≥ 15% Certificate available upon request on RureGold.com

TECHNICAL SPECIFICATIONS

PERFORMANCE SPECIFICATIONS	REQUIREMENTS IN ACCORDANCE WITH EN 998-2	PRODUCT PERFORMANCE SPECIFICATIONS
Compressive strength after 28 days	Between class M1 (≥ 1 MPa – 145 psi) and class Md (d > 20 MPa – 2900.75 psi as a multiple of 5)	≥ 20 MPa (2900.75 psi) M20
Modulus of elasticity in compression after 28 days	not requested	≥ 7.5 GPa (1088 ksi)
Chloride content	-	< 0.1%
Reaction to fire (Italian Ministerial Decree 10/03/2005)	-	Euroclass A1

APPLICATION DATA

Mixing water per 25 kg bag	approx. 5.5 - 6.5 litres
Mix consistency	Thixotropic
Application time at 20°C	Densification begins after approx. 10-15 minutes. Mix again and use within a maximum of about 45 minutes
Application temperature	From +5°C (41°F) up to +35°C (95°F)
Coverage	approx. 8.5 kg/m ² (1.74 lb/ft ²) per strengthening layer (3+3 mm) approx. 12.8 kg/m ² (2.62 lb/ft ²) per double strengthening layer (3+3+3 mm)
Packaging	Disposable wooden pallet laden with 60 x 25 kg (55.1 lb) bags - total weight 1500 kg (3306.9 lb)
Storage conditions (Regulation (CE) No. 1907/2006 – Annex XVII point 47)	In original packaging, indoors, in a cool, dry, unventilated place.
Durability (Regulation (CE) No. 1907/2006 – Annex XVII point 47)	Not more than 12 months from packing date.

SPECIFICATION ITEM

Supply and application of an FRCM structural strengthening system, consisting of a carbon fibre mesh and inorganic matrix, e.g. Ruregold **MX-C 25 Masonry**. The carbon fibre has a toughness/tensile strength of approx. 4.9 GPa (710.7 ksi), a maximum modulus of elasticity 250 GPa (36259,4 ksi), and a strain at rupture of 1.9%. The compressive strength of the inorganic matrix, which is specifically designed for masonry substrates, is ≥ 20 MPa (2900.75 psi), while the modulus of elasticity is ≥ 7.5 GPa (1087.8 ksi). The FRCM systems in carbon fibre may be used to strengthen load-bearing walls (piers) and spandrels, reinforce masonry corners, floor and ceiling edge beams, and the intrados and extrados of arch and vault structures, as well as for anti-overtum protection solutions on internal partition and external in-fill walls. The system is resistant to high temperatures and freeze/thaw cycles and may be applied directly to moist substrates. The system meets the requirements of the FRCM Guidelines issued in March 2022. The substrate must be prepared and the system applied in accordance with the manufacturer's instructions.

This technical data sheet is not a specification. The provided figures, and content thereof, are based on our best knowledge and experience, and are purely indicative in nature. The user is responsible for determining whether or not the product is suitable for the intended use, assuming all responsibility for its use and application. Laterlite reserves the right to change the packaging and the contained quantity without prior notice. Laterlite products are intended for professional use only. This Technical Data Sheet cancels and replaces previous editions, which are no longer in force. Check the latest revision on the RureGold.com website

Edition 08/2025 – Revision 01

